



Multi Chemical Laboratory-Physical Testing Team

TEST REPORT

Report No. : TE/2009/90240
Page No. : 1 OF 3
Date : 2009/10/16

MEGAVIEW SCIENCE CO., LTD.

P.O. BOX 30-063, TAICHUNG 40799, TAIWAN.

The following merchandise was submitted and identified by the client as:

Product Description : POLYESTER FABRIC, 50 DENIER.
Color : WHITE (BLEACHED).
Style/Item no : DC0901-W.
Sample submitted by : MEGAVIEW SCIENCE CO., LTD.
Received Date : 2009/09/23.
Testing Period : 2009/09/23 TO 2009/10/16.

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Required & Test Results :

Test Results :

For further details, please refer to the following page(s)

Mandy Liu / Team Leader
Signed for and on behalf of
SGS TAIWAN LTD

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Multi Chemical Laboratory-Physical Testing Team

TEST REPORT

Report No. : TE/2009/90240
Page No. : 2 OF 3
Date : 2009/10/16

Test Required & Test Results :

Tensile strength test

Test Method	:	ASTM D5035-95 Reapproved 2003
Test Equipment	:	UNIVERSAL TESTING MACHINE
Test Condition	:	Speed : 300 mm/min and Temp. 20±2°C
Light Condition	:	ASTM G154-CYCLEL 6-108 hours 8h UV at 60±3°C Black Panel Temperature; 4h Condensation at 50±3°C Black Panel Temperature
Test Result	:	Before light test After light test
A direction average value	:	6.67 kgf/cm 2.99 kgf/cm
B direction average value	:	5.15 kgf/cm 2.51 kgf/cm

Color fastness to light test

Test Method	:	ASTM G154-06 Cycle 6
Test Equipment	:	QUV Tester-UVB313
Test Condition	:	8h UV at 60±3°C Black Panel Temperature; 4h Condensation at 50±3°C Black Panel Temperature.
Test Result	:	At 108 hours Grade 2-3

Note 1: The test item was subcontracted to other SGS Laboratory.

Note 2: Color fastness-Key to Grade rating Grade 5 represents the best stain removal and Grade 1 the poorest stain removal.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.html. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TEST REPORT

Report No. : TE/2009/90240
Page No. : 3 OF 3
Date : 2009/10/16

SAMPLE PHOTO



END OF REPORT

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.